

Substrates

– Woven Fabrics

TENRON®

Product description

Woven fabrics made of TENRON continuous filament for engineered substrates and high-performance composites.



Article reference

WF (Woven Fabric), EX.:

WF BSB3_2,10.400.127.T2/2.14/14.IS65T

- Specific surface weight (gr/m²)
- Length of roll (m)
- Width of roll (cm)
- Weaving pattern
- Number of ends per cm in warp and weft
- Sizing reference of constituent filaments (*)

Physical properties

Volume density of constituent fibres
(according to ASTM C693)

2.600 g/cm³

Specific surface weight

From 210 up to 1.050 g/m²

Construction (weaving pattern)

Plain, twill, satin

Thermal properties (according to DIN ISO 7884)

Melting point

1.560 °C

Transition temperature

730 °C

Softening point

940 °C

Thermal resistance (% of residual values after 24 h ageing)

From -200°C up to 850°C

Sizing

Content, % weight (loss of ignition, LOI)

0,4 – 1,5 % (according to customer's request)

Moisture content, % weight

Less than 0,1 %

Resin (matrix) compatibility

Epoxy, polyester, vinylester, PA, PP, PEEK, BMI, etc..

Mechanical properties

Sized and dried roving

(according to ISO 3341:2000)

- Tensile strength: 66 80 cN/tex
(depending on the sizing formulation):
1.580 ... 2.000 MPa
- Elongation at break: 2,10%
- Tensile modulus (Young or E-modulus):
90 ... 100 GPa

Impregnated strand (according to ASTM D2343 or ISO 9163:2005)

- Tensile strength: 3.400 ... 3.600 MPa
- Tensile modulus (Young or E-modulus):
86 ... 97 GPa

Standard Packaging

The rolls are individually labeled and wrapped with stretched plastic film for protection and improved handling.

Width (m)

1,27 cm

Length (m)

Full package is about 400m/ roll

Benefits of TENRON in end-applications

Please see our website, under "applications".

Storage and usage conditions

ISOMATEX S.A. recommends storage in a cool and dry warehouse into the original packaging. For an optimal processing we recommend to use the product in ambient conditions (20 – 23 °C, 60 – 65% relative humidity). TENRON roving need to be kept in the workshop at least 24 hours prior to usage.

Sustainability

- ISOMATEX S.A. respects the environmental directives of the **European Union** and is **REACH compliant** (Regulation, Evaluation, Authorisation and Restriction of Chemicals) .
- TENRON is fully and easily recyclable. For more information on **sustainability** and our **LCA**, please see our website and / or contact us.

For more detailed information, please contact the Isomatex Sales Department at **info@isomatex.com** or by phone at the following number: **+32 (0)81.72.86.86**

DISCLAIMER OF LIABILITY

The data presented above is provided solely as a guide in the selection of fibre reinforcement. The information mentioned in this leaflet is based on actual ISOMATEX laboratory data and field test experience. Due to numerous factors in downstream processability that may affect results, we consider this information reliable but do not guarantee its applicability to the user's process or assume any liability arising from its use or performance. The end-user, by accepting the products described herein, assumes the responsibility for thoroughly testing any application to determine its compliance before committing to production. It is important for the end-user to determine the properties of their own commercial compounds when using this or any other fibre reinforcement.

WE MAKE NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. STATEMENTS AND DATA IN THIS DOCUMENT SHALL NOT BE INTERPRETED AS REPRESENTATIONS OR WARRANTIES OR AS INDUCEMENTS TO INFRINGE ANY PATENT OR VIOLATE ANY LAW, SAFETY CODE, OR INSURANCE REGULATION.

Strong by Nature

Scientific Park CREALYS
Rue Camille Hubert 29
5032 Gembloux, Belgium

☎ +32(0)81.72.86.86
✉ info@isomatex.com
🌐 www.isomatex.com