

# Pre-Impregnated – Towpreg

T E N R O N<sup>®</sup>

## Product description

Towpreg is a specialized material where individual fibres are pre-impregnated with resin along their length. Designed for enhanced control and precision in creating composite parts, especially in applications with fine-tuned fibre placement and minimal waste.

## Article reference

### Towpreg, EX.:

TOW MEDR BSB3\_1600-80(10).60.IS65T.CS01E

- Strand type (Single or Multi-End Direct roving) \_\_\_\_\_
- Batch composition's reference \_\_\_\_\_
- Linear density in TEX (gr/km), see below \_\_\_\_\_
- Linear density in TEX of constituent single-end roving \_\_\_\_\_
- Diameter of virgin (elementary) filaments (µm.) \_\_\_\_\_
- Resin content (%) \_\_\_\_\_
- Sizing reference(\*) \_\_\_\_\_
- Cardboard sleeve : • with felt surface or embossed- texture for external discharges \_\_\_\_\_  
• without cardboard sleeve for internal discharges

## Physical properties

### Volume density (ASTM C693)

2.600 gr/cm<sup>3</sup>

### Poisson ratio

0,24

## Thermal properties (according to DIN ISO 7884)

Linear coefficient of thermal expansion 20°...300°C,  
CTE (ASTM D696): 3,72 ... 4,9 \* 10<sup>-6</sup> /°C

### Melting point

1.560 °C

### Transition temperature

730 °C

### Softening point

940 °C

## Thermal resistance (% of residual values after 24h ageing)

From -200°C up to 850°C

## Sizing

### Content, % weight (loss of ignition, LOI)

0,4 – 1,5 % (according to customer's request)

### Moisture content, % weight

Less than 0,1 %

## Mechanical properties

### Sized and dried roving

(according to ISO 3341:2000)

- Tensile strength: 66 ... 80 cN/tex  
(depending on the sizing formulation):  
1.580 ... 2.000 MPa
- Elongation at break: 2,10%
- Tensile modulus (Young or E-modulus):  
90 ... 100 GPa

### Impregnated strand (according to ASTM D2343 or ISO 9163:2005: )

- Tensile strength: 3.400 ... 3.600 MPa
- Tensile modulus (Young or E-modulus):  
86 ... 97 Gpa

### Towpreg (according to ISO 527-4 )

- Depending on the impregnated woven fabric (available upon request)

### Resin (matrix) compatibility

Epoxy, polyester, vinylester.

### Fibre volume fraction

50 – 70%

(\*) see Isomatex Sales department for more information

## Standard Packaging

Standard packaging includes cylindrical bobbins with felt- or embossed surface sleeves.

Bobbins are individually labelled and wrapped with stretched plastic film for protection and improved handling.

### Height of cardboard sleeve (mm)

From 260 to 300 mm

### Inner diameter of cardboard sleeve (mm)

76 mm

## Benefits of TENRON in end-applications

Please see our website, under “applications”.

## Storage and usage conditions

ISOMATEX S.A. recommends storage in a cool and dry warehouse into the original packaging. For an optimal processing we recommend to use the product in ambient conditions (20 – 23 °C, 60 – 65% relative humidity). TENRON roving need to be kept in the workshop at least 24 hours prior to usage.

## Sustainability

- ISOMATEX S.A. respects the environmental directives of the **European Union** and is **REACH compliant** (Regulation, Evaluation, Authorisation and Restriction of Chemicals) .
- TENRON is fully and easily recyclable. For more information on **sustainability** and our **LCA**, please see our website and / or contact us.

For more detailed information, please contact the Isomatex Sales Department at **info@isomatex.com** or by phone at the following number: **+32 (0)81.72.86.86**

---

### DISCLAIMER OF LIABILITY

The data presented above is provided solely as a guide in the selection of fibre reinforcement. The information mentioned in this leaflet is based on actual ISOMATEX laboratory data and field test experience. Due to numerous factors in downstream processability that may affect results, we consider this information reliable but do not guarantee its applicability to the user's process or assume any liability arising from its use or performance. The end-user, by accepting the products described herein, assumes the responsibility for thoroughly testing any application to determine its compliance before committing to production. It is important for the end-user to determine the properties of their own commercial compounds when using this or any other fibre reinforcement.

WE MAKE NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. STATEMENTS AND DATA IN THIS DOCUMENT SHALL NOT BE INTERPRETED AS REPRESENTATIONS OR WARRANTIES OR AS INDUCEMENTS TO INFRINGE ANY PATENT OR VIOLATE ANY LAW, SAFETY CODE, OR INSURANCE REGULATION.

---

Strong by Nature

Scientific Park CREALYS  
Rue Camille Hubert 29  
5032 Gembloux, Belgium

☎ +32(0)81.72.86.86  
✉ info@isomatex.com  
🌐 www.isomatex.com